

008060-0685960

We claim:

- Sub
A
1. A covalently polymerized, water-absorbing, hydrogel-forming material,
wherein the material has both hydrophilic and hydrophobic regions and
is characterized as having the following properties:
 - a) absorbing water to less than about 300% of its initial weight, on equilibration with water or bodily liquids;
 - b) having a solids content of at least about 20% after equilibration in water or bodily liquids;
 - c) having an elongation to failure of at least about 25% hydration to equilibrium; and
 - d) being sufficiently biocompatible to permit the treatment or repair of biological tissue, or used as an implant in a patient.
 2. The material of claim 1, having a molecular weight after polymerization of at least 10 kDa.
 3. The material of claim 1, which is covalently crosslinked.
 4. The material of claim 1, which is non-covalently crosslinked.
 5. The material of claim 1, having a tensile modulus of at least about 50 kPa after equilibrium hydration.
 6. The material of claim 1, having an equilibrium water content of at least about 2%.
 7. The material of claim 1, being capable of being formed *in situ* on body tissue or a medical implant by one or both of polymerization and crosslinking.
 8. The material of claim 1, adhering to tissue when polymerized thereon.
 9. The material of claim 1, being substantially elastic during a 10% elongation and release therefrom.

wherein at least about 40% by weight of the monomers consists of amphiphilic monomers;

wherein no more than about 50% by weight of the monomers consists of functionally hydrophobic monomers;

- b) 0% to about 40% by weight of a reactive macromer having a molecular weight greater than about 500 Da, which comprises on average more than one polymerizable group per molecule, and which has hydrophilic groups comprising about 20% of the macromer; and
- c) 0% to about 40% water.

19. The material of claim 1 in the form of a coating on an implant or device.

20. The material of claim 1 forming an implant or device.

21. A monomer having the formula AHK, wherein:

A is a residue of an ethylenically unsaturated acid that is linked to H by a bond selected from ester and amide;

H is the residue of a hydroxy carboxylic acid, a carbonic acid, or an amino acid, which is linked to K by an ester bond; and

K is the residue of an alcohol containing at least one carbon atom.

22. The monomer of claim 21 wherein

A is selected from the group consisting of acrylic, methacrylic crotonic, isocrotonic, tiglic, angelic, and cinnamic acids; maleic, fumaric, citraconic, mesaconic, itaconic, citric and isocitric acids, and monoesters and monoamides thereof, and mixtures thereof;

H is selected from the group consisting of glycolic acid, lactic acid, 3-hydroxy-propanoic acid, a hydroxybutyric acid, a hydroxypentanoic acid, hydroxy trimethylene carbonic acid, hydroxy ethylene carbonic acid, hydroxy propylene carbonic acid, hydrolyzed dioxanone (i.e., 2-hydroxyethoxyacetic acid), a hydroxyhexanoic acid,

an alpha, beta or gamma amino acid of eight carbons or fewer, and mixtures thereof; and

K is an alcohol containing from 1 to about 10 carbon atoms and at least one hydroxyl group, or a mixture of such alcohols.

23. The monomer of claim 22 wherein A is selected from the group consisting of acrylic acid and methacrylic acid.

24. The monomer of claim 22 wherein H has one to about eight carbon atoms and is selected from the group consisting of glycolic acid, lactic acid, 3-hydroxy-propanoic acid, a hydroxybutyric acid, a hydroxypentanoic acid, and a hydroxyhexanoic acid.

25. The monomer of claim 22 wherein H is selected from the group consisting of hydroxy trimethylene carbonic acid, hydroxy ethylene carbonic acid, hydroxy propylene carbonic acid, and hydrolyzed dioxanone (i.e., 2-hydroxyethoxyacetic acid).

26. The monomer of claim 22 wherein H has two to eight carbon atoms and is selected from the group consisting of an alpha amino acid, a beta amino acid, a gamma amino acid, and mixtures thereof.

27. The monomer of claim 22 wherein K is selected from the group consisting of methanol, ethanol, propanol, isopropanol, isomers of butanol, isomers of pentanol, and isomers of hexanol.

28. An intermediate for the preparation of the monomer of claim 21, the intermediate having the form AHC wherein A is a residue of an ethylenically unsaturated acid that is linked to H by a bond selected from ester and amide;

H is the residue of a hydroxy carboxylic acid, a carbonic acid, or an amino acid, which is linked to C by an acyl bond; and

C is a leaving group, which is displaced by alcohols to form esters.

[illegible]

Sub ~~133~~ from
m

The intermediate of claim 1, consisting of glycolic acid, hydroxybutyric acid, a hydroxy carbonic acid, hydroxy carbonic acid, hydrolyzed hydroxyhexanoic acid, an aliphatic compound having one or fewer, and mixtures thereof.

The material of claim 1, consisting of acrylic acid and

37. A method for the treatment of biological tissue or a medical implant comprising the application of a crosslinked polymeric

008060" 06E85960

hydrogel material to the tissue or implant, wherein the material has both hydrophilic and hydrophobic regions and is characterized as having the following properties:

- a) absorbing water to less than about 300% of its initial weight, on exposure to water or bodily liquids;
- b) having a solids content of at least about 20% after equilibration in water or bodily fluids;
- c) having an elongation to failure of at least about 25% both as formed and after swelling to equilibrium; and
- d) being biocompatible;

wherein the material is formed by the crosslinking of reactive monomers and macromers in the presence of tissue, and undergoes hydration with bodily liquids to form a water-containing material.

[Handwritten signature]
[Handwritten initials]